



PU 302 FC40

TECHNICAL INFORMATION FORM

1 – DESCRIPTION

PU 302 is a one-component, high-modulus polyurethane sealant that cures on exposure to atmospheric humidity. It possesses excellent adhesion to sheet iron, aluminum, stainless steel, lead, copper, ceramic, glass, wood and various plastic materials.

2 – PROPERTIES

- Permanently flexible
- Non-sag consistency - Exceptional thixotropy
- Non-sticky / does not pick up dirt
- Minimal shrinkage
- Improved storage stability
- Easy to gun, can be easily smoothed
- Over-paintable

3 - APPLICATIONS

- Body construction of cars, containers, caravans etc.
- Sealing and bonding of ventilation ducts, gutters and spouts etc.
- Sealing of sheet metal seams
- For vibration reduction in all type of sheet metal assembly works
- Sealing against water, air, gas and dust.

4 - INSTRUCTIONS

- Surface preparation: Joint surfaces must be dry, clean and free of all contamination. Glass, metal and other non-porous surfaces must be free of any coatings and wiped clean with solvent.
- Cut opens the cartridge, screw on nozzle and cut off tip at desired angle. Take off the aluminum cover at the bottom of the cartridge. Insert cartridge in gun and apply the sealant bubble-free continuously into the joint. Fill the joint completely. Smoothen it by pressing with a spatula or similar apparatus.

Joint width	15 mm	20 mm	25 mm	30 mm	35 mm
Joint Depth	8 mm	10 mm	12 mm	15 mm	15 mm
Joint length / 600 ml	5 meters	3 meters	2 meters	1,3 meters	1,1 meters

5- STORAGE AND SHELF LIFE

12 months if stored properly in its original package.

6- PACKAGING

Product	Volume	Package
White / Black / Grey	310ml	12
White / Black / Grey	600ml	12

7- RESTRICTIONS

- Avoid application below 5 °C and above 40 °C.
- Do not apply on frozen or wet surfaces or through standing water.

8- TECHNICAL PROPERTIES

BEFORE CURING	
Basis	: Polyurethane
Consistency	: Thixotropic
Curing Mechanism	: Moisture Curing
Density	: 1,18± 0,03 g/ml
Skin formation time	: 40 ± 10 min. (23°C and 50% R.H)
Curing Rate	: Min. 3 mm/day (23°C and 50% R.H)
Sagging	: 0 mm (EN ISO 7390)
Temperature Resistance	: -40°C to +90°C
Application Temperature	: +5°C to +40°C
AFTER CURING	
Hardness Shore A	: 35-40 After 28 days
Paintibility	: Yes *
MECHANICAL PROPERTIES (ISO 8339)	
Elongation at break	: Min. 350%
Tensile Strength	: Min 2.0 N/mm ²

*Considering the diversity of paint base and quality, compatibility tests should be done before application.

LEGAL WARNING

The information provided here on ADROIT products, and in particular the recommendations regarding their application and end-use, are given in good faith based on ADROIT's current knowledge and experience when these products are properly stored, handled and applied under normal conditions and in line with ADROIT's recommendations.

Products, application surfaces and application areas are quite diverse in practice. For this reason, when using ADROIT products, be sure to apply the right product in the right conditions and in the right place, and strictly follow the information and instructions given by ADROIT regarding commercial availability and/or fitness for a particular purpose. Otherwise, ADROIT is not responsible for any damages that may occur.

The user (user) of the product should test the suitability of the product for the application and purpose for which he intends to use the product. ADROIT reserves the right to change the features of its products. The property rights of third parties must be respected.

Acceptance of all orders is based on our current terms of sale and shipping. Users should always consider the latest edition of the local Product Information File of the relevant product, which can be obtained by contacting ADROIT.

ADROIT