



PU 201

TECHNICAL DATA SHEET

1 – DESCRIPTION

PU 201 WINDSHIELD ADHESIVE is single part polyurethane based, high modulus sealant, which cures on exposure to atmospheric moisture to form elastomeric adhesive.

PU 201 WINDSHIELD ADHESIVE has high bonding strength, oil resistance, aging resistance, salt fog resistance, and can bear long time vibration.

PU 201 WINDSHIELD ADHESIVE offers excellent adhesion on glass and metal, it is most suitable for bonding windshield in the automotive industry.

2 – PROPERTIES

- **High initial bond strength on glass and metal surfaces**
- One component formulation
- Good non-sag properties
- Non-corrosive to substrates
- High mechanical performance
- High Modulus & tensile strength
- Can be overpainted

3 - APPLICATIONS

- Used for sealing for automotive windscreen, windows and scuttles.
- Also suitable for sealing in automotive, caravan, ship building and railway industry.
- Suitable for sealing, seam sealing, simple bonding as well as for vibration reduction and sound deadening measures
- In crash body repair and car body construction.

4 - INSTRUCTIONS

- Remove the damaged glass. Before application ensure that surfaces are clean, dry and free from dust and grease.
- Shake the Polyurethane Windshield Adhesive Primer for at least 30 seconds (after hearing the ball move) before application.
- Apply Windshield Adhesive Primer to the outer edge of the glass where the urethane bond will be made and allow to dry.
- Ensure that primer is tack-free dry before proceeding.
- Cut tip of the nozzle to desired dimension and size to provide a bead height sufficient to give good contact with the windshield around the entire perimeter. A triangular shaped notch will provide the optimal bead shape and height.
- It is recommended to apply the adhesive with a pneumatic sealant gun.

- Position the glass by aligning the masking tape on glass and car body. Press glass in place to assure complete contact with the Polyurethane Windshield Adhesive

5- STORAGE AND SHELF LIFE

9 months if stored properly in its original package between +5 °C and 30 °C, 50% humidity.

6- PACKAGING

Product	Volume	Package
Black	310ml	12
Black (Sausage)	600ml	12

7- RESTRICTIONS

- Avoid application below 5 °C and above 40 °C.
- Do not apply on frozen or wet surfaces or through standing water.

8- TECHNICAL PROPERTIES

BEFORE CURING		
Basis	: Polyurethane	
Consistency	: Thixotropic	
Curing Mechanism	: Moisture Curing	
Density	: 1,17±0,03 g/ml	
Curing rate	: Min. 3,5 mm/24 h	
Tack free time	: 30±10 min. (23°C and 50% R.H)	
Sagging	: 0 mm	(EN ISO 7390)
AFTER CURING		
Hardness Shore A	: 60 ±5	After 7 days
Paintability	: Yes *	
Elongation at break	: Min. 400%	(ASTM D412)
Tensile Strength	: Min. 5.5 MPa	(ASTM D412)
Solid Content	: ≥98	

*Considering the diversity of paint base and quality, compatibility tests should be done before application.

LEGAL WARNING

The information provided here on ADROIT products, and in particular the recommendations regarding their application and end-use, are given in good faith based on ADROIT's current knowledge and experience when these products are properly stored, handled and applied under normal conditions and in line with ADROIT's recommendations.

Products, application surfaces and application areas are quite diverse in practice. For this reason, when using ADROIT products, be sure to apply the right product in the right conditions and in the right place, and strictly follow the information and instructions given by ADROIT regarding commercial availability and/or fitness for a particular purpose. Otherwise, ADROIT is not responsible for any damages that may occur.

The user (user) of the product should test the suitability of the product for the application and purpose for which he intends to use the product.

ADROIT reserves the right to change the features of its products. The property rights of third parties must be respected.

Acceptance of all orders is based on our current terms of sale and shipping. Users should always consider the latest edition of the local Product Information File of the relevant product, which can be obtained by contacting ADROIT.